


# Waterstop

## HyDra Elastomer AM corner

### type A & W



#### **PRODUCT\* SPECIFICATION**

Waterstop HyDra Elastomer expansion waterstop series AM corners A & W according to DIN 7865, part 1 and 2 is a permanently flexible profile with middle tube made of elastomer, SBR or EPDM, that is used to seal construction joints in waterproof concrete structures with high water pressures.

#### **Characteristics / Advantages**

- high tensile strength and elongation at break
- high permanent flexibility and high-load bearing capacity
- suitable for water pressure and large settlements
- resistant to all natural media acting aggressively to concrete
- resistant to a wide range of chemical substances (tests required for each additional specific situation)
- resistant to bitumen
- supply of systems for easy handling on site
- vulcanizable by using butt joints on site

#### **Application**

- joint sealing in concrete structures
- expansion joint sealing system for in-situ concrete

#### Typical structures

- commercial buildings, cellars, bridges, trough and bridge constructions
- rail tunnels and road tunnels
- water construction plants

# Waterstop HyDra Elastomer AM corner type A & W

## **Standards / Directives**

- DIN 18197
- DIN 7865, part 2
- WU-Directives DAfStb
- ZTV-ING, Riz-Ing
- Vulcanizing instructions

## **Test certificate / Approvals**

- latest manufacturer's test certificate
- certificate of conformity - DIN 7865
- external monitoring by MPA NRW
- internal monitoring

## **PRODUCT DATA**

### **Material**

- SBR elastomer (styrene butadiene rubber)
- EPDM elastomer (ethylene-propylene-diene monomer)

### **Colour**

- black

### **Packaging**

- supplied as standard rolls (25 m), pre-cut parts and systems

# Waterstop

## HyDra Elastomer AM corner

### type A & W

---

#### MECHANICAL PROPERTIES



according to DIN 7865, Part 2

<b>Shore A hardness</b>	$62 \pm 5$
<b>Tear strength</b>	$\geq 10 \text{ MPa}$
<b>Elongation at break</b>	$\geq 380 \%$
<b>Compression set</b>	168h / 23°C $\leq 20\%$ 24h / 70°C $\leq 35\%$
<b>Tear propagation resistance</b>	$\geq 8 \text{ kN/m}$
<b>Performance after heat ageing</b>	Shore A hardness change $\leq 8$ Tear strength $\geq 9 \text{ MPa}$ Elongation at break $\geq 300\%$
<b>Low temperature performance</b>	$\leq 90 \text{ Shore A}$
<b>Tension set</b>	$\leq 20\%$
<b>Performance after conditioning in hot bitumen</b>	Residual deformation $< 20\%$ Tear strength $\geq 7 \text{ MPa}$ Elongation at break $\geq 300\%$
<b>Performance after ozone ageing</b>	No cracks



---

## Waterstop HyDra Elastomer AM corner type A & W

AM 250 Ecke A





AM 250 Ecke W





All dimensions in mm

## Waterstop HyDra Elastomer AM corner type A & W

AM 350 Ecke A



AM 350 Ecke W



All dimensions in mm